

KPNOX 18



PICKLING GEL FOR STAINLESS STEEL

Made in / Fabriqué au Canada 🇨🇦

Eliminates impurities and restores resistance to corrosion. KPNOX¹⁸ is tough on oxide scale and stains that form in weld zones and leave no white stain behind. It is free of hydrofluoric and nitric acid and virtually odorless.

TO ORDER

PRODUCT CODE	FORMAT	CURRENT PRICE
KP-1802GEL-1G	2L	
KP1802GEL-20G	20L	

DIRECTIONS

Mix well. Apply a uniform layer on welds with a non-metallic brush OR spray surface using stainless steel paint gun. Let stand 15-90 minutes. Reaction time can vary depending on metal grade, surface finish, welding process and ambient temperature. Rinse using high-pressure water jet.

STORAGE AND HANDLING

Store in a cool, well-ventilated area. Keep away from heat, sparks and flames. Keep away from caustic solutions and alkaline reducing agents. Keep containers well closed. Fast-opening packaging is compliant with UN standards.

NEUTRALIZATION METHOD

Residues and contaminated water must be neutralized to pH6-8. Heavy metals released in the cleaning of stainless steel must be disposed of, along with residues and neutralized solutions, in facilities authorized to treat hazardous waste in compliance with applicable regulations.

PRECAUTIONS

Wear rubber boots, impervious gloves, a plastic apron and protective glasses. Avoid all contact with skin. Keep away from sources of ignition. Handle in a well-ventilated area or wear a suitable breathing apparatus. Use non-metallic tools.

FIRST AID

In case of discomfort, move to well-ventilated area. If a person has stopped breathing, administer artificial respiration and get medical attention. In case of contact with eyes, flush thoroughly with water and get medical attention. See Safety Data Sheet.

For more information about our products and customized solutions, or for a free demonstration, contact us:

T. 1-514-333-0754 | E. info@gkemplus.com
F. 1-514-333-5780 | W. gkemplus.com

6020 Vanden Abeele, Saint-Laurent, Québec, Canada H4S 1R9